

L & M Supply Co., Inc.

P.O. Box 640

Willacoochee, GA 31650

Phone: 800-948-7870 Fax: 912-534-6254

L & M Woven Stabilization Geotextile Fabric

Property	Test Method	L & M 150 lb	L & M 200 lb	L & M 300 lb
Grab Tensile- MD lbs	ASTM-D-4632	150	210	360
Grab Tensile- CD lbs	ASTM-D-4632	120	208.5	300
Grab Elongation %	ASTM-D-4632	15	15	15
Mullen Burst psi	ASTM-D-3786	300	400	675
Puncture lbs	ASTM-D-4833	84	95	150
Trapezoidal Tear lbs	ASTM-D-4533	-	88	120
UV Resistance %@hrs	ASTM-D-4355	70@2500	70@2500	70@2500
Permittivity sec ⁻¹	ASTM-D-4491	0.05	0.08	0.05
AOS Sieve	ASTM-D-4751	-	50	40
Flow Rate gal/min/ft ²	ASTM-D-4491	34	5	4
Roll Width ft.		15	12.5/15/17.5	12.5/15/17.5
Roll Area yd ²		500	500 /600	500

Values above may have a tolerance of +/- 5%